

Intergard[®] 475HS

High anti-corrosive performance and more

Do you want more than long term corrosion protection from your intermediate? How about high solids, low VOCs and an extended overcoating interval?

Used on the Sydney Harbour Bridge, Intergard[®] 475HS is the ideal choice in providing project flexibility and protecting assets in tough environments.

What more do you need?

- High solids epoxy intermediate
- Micaceous Iron Oxide variant for additional barrier protection
- 200µm (8 mils) dft possible in one coat
- Low VOC
- Approved for use in NORSOK M501 System 1 specifications
- Designed to provide optimum adhesion for top coats



AkzoNobel

This combination of economics and environmental responsibility makes Intergard 475HS the ideal product for use in fabrication shops

Intergard 475HS has been formulated to accommodate the trend towards environmentally responsible coatings whilst not compromising the overall cost of the coating system. The high solids formulation allows the application of Intergard 475HS at 200 microns (8 mils) as an intermediate coat, thus eliminating a full coat of paint from those conventional specifications which call for 2 coats of epoxy intermediate.

Intergard 475HS is typically applied over epoxy, zinc epoxy or inorganic zinc primers as part of a multi-coat system for steel surfaces such as:

- Offshore platforms
- Mining Conveyors
- Bridges
- Structural Steel
- Cranes
- Wind Turbines

Technical Information

Colour	Light grey MIO and a selected range of colours	
Gloss Level	Matt	
Volume Solids	80%	
Film Thickness	125-200µm (5-8 mils) dry	
Mix Ratio	3:1 by Volume	
Temperature	Touch Dry	Min Recoat
5°C (41°F)	90 minutes	16 hours
15°C (59°F)	75 minutes	10 hours
25°C (77°F)	60 minutes	5 hours
VOCs	92g/kg 1.72lb/gal (207g/l)	EU Solvent Emissions Directive (Council Directive 1999/13/EC) USA - EPA Method 24

Test Data

	TEST METHOD	SPECIFICATION DETAILS	RESULTS
Hardness	ASTM D3363 - "Film hardness by Pencil Test"	1 x 200µm (8 mils) dft applied directly to Sa2.5 (SSPC-SP6) blasted steel	Classification 4H
Impact	ASTM D2794 - "Resistance to the Effects of Rapid Deformation (Impact)"	1 x 200µm (8 mils) dft applied directly to Sa2.5 (SSPC-SP6) blasted steel	Direct Impact Resistance - 3.2 Joules
Adhesion	ISO 4624	1 x 200µm (8 mils) dft applied directly over epoxy primer	Not less than 12 MPa (1740 psi)
Salt Spray	ISO 7253	1 x 200µm (8 mils) dft applied over zinc rich epoxy primer	No film defects and no rust creep at the scribe after 4000 hours

The above performance data has been compiled based on present experience of in-service product performance and upon performance data obtained under laboratory test conditions. Actual performance of the product will depend upon the conditions in which the product is used.

www.international-pc.com
protectivecoatings@internationalpaint.com

✘ and **International** and all product names mentioned in this publication are trademarks of, or licensed to, Akzo Nobel. © AKZO NOBEL 2009.

International Protective Coatings has used its best endeavours to ensure that the information contained in this publication is correct at the time of printing. Please contact your local International Protective Coatings representative if you have any questions.

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale.