

**PRODUCT DESCRIPTION**

A three component, metallic, zinc rich epoxy primer which passes Slip B coefficient. Interzinc 315B complies with SSPC Paint 20 and contains minimum 80% zinc in the dry film.

The zinc dust used in Interzinc 315B conforms to ASTM D520, Type II.

**INTENDED USES**

As a high performance primer to give maximum protection as part of any anti-corrosive coating system for aggressive environments including those found on bridges, offshore structures, petrochemical facilities, pulp and paper plants and power plants.

Interzinc 315B has been designed to provide excellent corrosion resistance in both maintenance and new construction situations.

**PRACTICAL INFORMATION FOR INTERZINC 315B**

<b>Color</b>	Green, Red
<b>Gloss Level</b>	Matte
<b>Volume Solids</b>	68%
<b>Typical Thickness</b>	2-6 mils (50-150 microns) dry equivalent to 3-8.8 mils (74-221 microns) wet
<b>Theoretical Coverage</b>	364 sq.ft/US gallon at 3 mils d.f.t and stated volume solids 9.10 m <sup>2</sup> /liter at 75 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Air Spray, Brush

**Drying Time**

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
32°F (0°C)	15 hours	30 hours	30 hours	Extended <sup>1</sup>
41°F (5°C)	1 hour	7 hours	7 hours	Extended <sup>1</sup>
59°F (15°C)	40 minutes	4 hours	4 hours	Extended <sup>1</sup>
77°F (25°C)	30 minutes	3 hours	30 minutes	Extended <sup>1</sup>
104°F (40°C)	15 minutes	1.5 hours	30 minutes	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions & Abbreviations

**REGULATORY DATA**

<b>Flash Point</b>	Part A 84°F (29°C); Part B 76°F (25°C); Mixed 84°F (29°C)	
<b>Product Weight</b>	27.2 lb/gal (3.26 kg/l)	
<b>VOC</b>	2.42 lb/gal (290 g/l)	EPA Method 24

See Product Characteristics section for further details

**SURFACE PREPARATION**

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

**Abrasive Blast**

Abrasive blast clean to a minimum of SSPC-SP6 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Interzinc 315B, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

A surface profile of 2-3 mils (50-75 microns) is recommended.

**Shop Primed Steel**

Interzinc 315B is suitable for application to steelwork freshly coated with zinc silicate shop primers.

If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

**APPLICATION**

<b>Mixing</b>	Material is supplied in three containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1) Agitate Part A, then combine the entire contents of Part A and Part B and mix thoroughly with a power agitator.			
	(2) Part C, the powder component, should be slowly added to the thoroughly mixed Part A and Part B whilst stirring with a power agitator.			
	(3) Material should be sieved prior to application and should be constantly agitated in the pot during spraying.			
<b>Mix Ratio</b>	1.9 part(s) : 0.71 part(s) : 1.43 part(s) by volume			
<b>Working Pot Life</b>	41°F (5°C) 8.5 hours	59°F (15°C) 5 hours	77°F (25°C) 3 hours	104°F (40°C) 1 hour
<b>Airless Spray</b>	Recommended	Tip Range 17-21 thou (0.43-0.53 mm) Total output fluid pressure at spray tip not less than 2503 psi (176 kg/cm <sup>2</sup> )		
<b>Air Spray (Pressure Pot)</b>	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
<b>Brush</b>	Suitable - Small areas only	Typically 2.0-3.0 mils (50-75 microns) can be achieved		
<b>Roller</b>	Not recommended			
<b>Thinner</b>	International GTA415	Do not thin more than allowed by local environmental legislation		
<b>Cleaner</b>	International GTA415			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA415. Once units of paint have been mixed, they should not be resealed and it is advised that after prolonged stoppages, work recommence			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA415.			
	It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency should depend upon amount sprayed, temperature and elapsed time, including any delays.			
	all surplus material and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

**PRODUCT CHARACTERISTICS**

The film thickness of Interzinc 315B applied must be compatible with the blast profile achieved during surface preparation.

Care should be exercised during application to avoid over-application which may result in cohesive film failure with subsequent high builds, and to avoid dry spray which can lead to pinholing of subsequent coats.

Over-application of Interzinc 315B will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

Interzinc 315B is not recommended for underwater use.

Interzinc 315B is suitable for the localized repair of damaged inorganic zinc primer - consult International Protective Coatings for specific advice.

Interzinc 315B is approved by NEPCOAT as the primer for the following system:

Interzinc 315B  
Intergard 475HS  
Interthane 870UHS.

Note: VOC values quoted are based on maximum possible for the product taking into account variations due to color differences and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also effect VOC values determined using EPA Method 24.

**SYSTEMS COMPATIBILITY**

---

Interzinc 315B is designed for application to correctly prepared steel. It is possible to apply over approved prefabrication primers. Details of these can be obtained from International Protective Coatings.

Recommended topcoats are:

Intergard 345	Intergard 475HS
Interseal 670HS	Interthane 870
Interthane 870UHS	Interthane 990
Interthane 990FD	Interthane 990HS
Interzone 954	

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B		Part C	
		Vol	Pack	Vol	Pack	Vol	Pack
	4 US gal	1.9 US gal	5 US gal	0.7 US gal	1 US gal	1.4 US gal	5 US gal
For availability of other pack sizes contact International Protective Coatings							
SHIPPING WEIGHT	Unit Size	Part A		Part B		Part C	
		23.8 lb		6.2 lb		84.6 lb	
STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.					

**Disclaimer**

*The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. THEREFORE, UNLESS WE SPECIFICALLY AGREE IN WRITING TO DO SO, WE DO NOT ACCEPT ANY LIABILITY AT ALL FOR THE PERFORMANCE OF THE PRODUCT OR FOR (SUBJECT TO THE MAXIMUM EXTENT PERMITTED BY LAW) ANY LOSS OR DAMAGE ARISING OUT OF THE USE OF THE PRODUCT. WE HEREBY DISCLAIM ANY WARRANTIES OR REPRESENTATIONS, EXPRESS OR IMPLIED, BY OPERATION OF LAW OR OTHERWISE, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

Copyright © AkzoNobel, 12/7/2010.

 Copyright © AkzoNobel, 12/7/2010.

[www.international-pc.com](http://www.international-pc.com)